



SECTION B-B
NOT TO SCALE

GENERAL NOTES:

1. USE MONOLITHIC CONSTRUCTION 4" THICK EXCEPT AT DRIVEWAYS WHERE THICKNESS OF 7" IN COMMERCIAL AND INDUSTRIAL ZONE AREAS AND 6" IN RESIDENTIAL ZONE AREAS IS REQUIRED.
2. PLACE CONTROL JOINTS AT 10 FOOT INTERVALS (MAXIMUM).
3. PLACE EXPANSION-CONTRACTION JOINTS (JOINT FILLER MATERIAL) THE FULL DEPTH OF CONCRETE PLUS 1 INCH. JOINT FILLER SHALL BE PLACED FLUSH WITH TOP OF CONCRETE, EVERY 50 FEET, FOR BOTH "FORMED" OR "SLIPPED FORMED" SIDEWALK. JOINT MATERIAL SHALL ALSO BE PLACED AT ALL INTERSECTIONS WITH PERPENDICULAR SIDEWALKS AND AT DRIVEWAYS.
4. EDGE SIDEWALK AND EXPANSION JOINTS WITH 1/2" RADIUS EDGING TOOL.
5. USE 4" MIN. THICK BASE COURSE COMPACTED TO 95% AVERAGE OF THE MAXIMUM DRY DENSITY. (ASTM D698)
6. CONCRETE FOR SIDEWALK SHALL BE IN ACCORDANCE WITH THE CITY OF CEDAR HILLS STANDARD CONCRETE SPECIFICATION.
7. CONTRACTOR SHALL BACKFILL AROUND CURB, GUTTER, AND SIDEWALK TO THE FINISHED GRADE LEVEL PRIOR TO THE ACCEPTANCE BY THE CITY. BACKFILL SHALL EXTEND 18" BEYOND OUTSIDE OF CURB, GUTTER, AND SIDEWALK.
8. IF SIDEWALK IS REPLACED, THE MINIMUM SECTION LENGTH SHALL BE 4 FEET.
9. NO EXCESS CONCRETE SHALL BE ALLOWED TO EXTEND ABOVE THE LEVEL PLANE OF THE BOTTOM SURFACE OF THE SIDEWALK.



CEDAR HILLS

STANDARD
DRAWING NO.

208

CONCRETE SIDEWALK